

## GEOTEXTILES TIPPTEX NON-WOVEN



Grade	Tensile Strength MD / CD EN ISO 10319  kN/m	Elongation at break MD / CD EN ISO 10319  %	Thickness At 2 kPa  EN ISO 9863	Static Puncture (CBR test)  EN ISO 12236  kN
BS 16	16,0 / 17,5	45 / 55	1,4	2,8

Dynamic Perforation Test (cone drop) EN ISO 13433  mm	Pore Size, O <sub>90</sub> EN ISO 12956  mm	Water Permeability Normal to the plane, V <sub>I</sub> H <sub>50</sub>  m / s
23	0,09	0,06



Grade	Mass / m <sup>2</sup> g/m <sup>2</sup> EN ISO 9864	Roll Width m	Roll Length m	Roll Diameter cm	Weight kg	Area m <sup>2</sup>
BS 16	200	4 or 5	100	40	80 or 100	400 or 500